

Eastman TRITAN™

copolyester

Enhanced capability injection molding material

Eastman Tritan™ copolyester provides customers a clear polymer product with a balance of performance and processability. This balance helps Tritan create exciting opportunities to differentiate your products through lasting aesthetic appeal and value. Some advantages include excellent toughness, chemical resistance, higher temperature resistance, low and stable shrinkage rates. Mold release and nonmold release versions are available as well as colors and UV additives.

- Excellent chemical resistance
- Excellent toughness
- Ease of processing
 - Easy-dry resin
 - Improved cycle time
 - Same mold shrinkage value as polycarbonate
- Good optical properties
- Higher temperature resistance
- Performs well in secondary operations

Basic properties

Property	ASTM method	Eastman Tritan™ copolyester	
		TX1000 and TX1001	TX2000 and TX2001
Specific gravity	D792	1.18	1.17
Mold shrinkage, in./in. or mm/mm	D955	0.005–0.007	0.005–0.007
Tensile stress @ yield, psi (MPa)	D638	6,200 (43)	6,400 (44)
Tensile stress @ break, psi (MPa)	D638	7,700 (53)	7,700 (53)
Elongation @ tensile break, %	D638	210	140
Flexural modulus, psi (MPa)	D790	225,000 (1,550)	228,000 (1,585)
Rockwell hardness, R scale	D785	112	115
Notched Izod impact strength @ 23°C (73°F), ft-lb/in. (J/m)	D256	18.4 (980)	12.2 (650)
Notched Izod impact strength @ -40°C (-40°F), ft-lb/in. (J/m)	D256	2.1 (110)	2.4 (126)
Deflection temperature @ 66 psi (0.455 MPa), °C (°F)	D648	99 (210)	109 (228)
Deflection temperature @ 264 psi (1.82 MPa), °C (°F)	D648	85 (185)	92 (198)

Suggested drying and processing conditions

Drying conditions	
Drying temperature, °C (°F)	88 (190)
Drying time, hr	4
Dryer air dew point, °C (°F)	< -29 (< -20)
Machine conditions	
Injection speed	slow
Screw speed, rpm	30–60
Pack and hold pressure, MPa	35–50
Cushion, in.	0.2–0.4
Back pressure, MPa	10–15

Processing temperatures	
Zones, °C (°F)	
Rear	Set barrel temperatures to reach target melt temperature, up to 10°–20°C (20°–40°F) below target depending on shear heating.
Center	
Front	
Nozzle, °C (°F)	282 (540)
Hot runners, °C (°F)	282 (540)
Melt temperature, °C (°F)	282 ± 10 (540 ± 20)
Mold temperature, °C (°F)	38°–66°C (100°–150°F)



The results of insight™

**Eastman Chemical Company
Corporate Headquarters**

P.O. Box 431
Kingsport, TN 37662-5280 U.S.A.

Telephone:
U.S.A. and Canada, 800-EASTMAN (800-327-8626)
Other Locations, (1) 423-229-2000
Fax: (1) 423-229-1193

Eastman Chemical Latin America

9155 South Dadeland Blvd.
Suite 1116
Miami, FL 33156 U.S.A.

Telephone: (1) 305-671-2800
Fax: (1) 305-671-2805

Eastman Chemical B.V.

Fascinatio Boulevard 602-614
2909 VA Capelle aan den IJssel
The Netherlands

Telephone: (31) 10 2402 111
Fax: (31) 10 2402 100

**Eastman (Shanghai) Chemical
Commercial Company, Ltd. Jingan Branch**

1206, CITIC Square
No. 1168 Nanjing Road (W)
Shanghai 200041, P.R. China

Telephone: (86) 21 6120-8700
Fax: (86) 21 5213-5255

Eastman Chemical Japan Ltd.

MetLife Aoyama Building 5F
2-11-16 Minami Aoyama
Minato-ku, Tokyo 107-0062 Japan

Telephone: (81) 3-3475-9510
Fax: (81) 3-3475-9515

Eastman Chemical Asia Pacific Pte. Ltd.

#05-04 Winsland House
3 Killiney Road
Singapore 239519

Telephone: (65) 6831-3100
Fax: (65) 6732-4930

www.eastman.com

Although the information and recommendations set forth herein are presented in good faith, Eastman Chemical Company makes no representations or warranties as to the completeness or accuracy thereof. You must make your own determination of their suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. Nothing contained herein is to be construed as a recommendation to use any product, process, equipment, or formulation in conflict with any patent, and we make no representations or warranties, express or implied, that the use thereof will not infringe any patent. NO REPRESENTATIONS OR WARRANTIES, EITHER EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR OF ANY OTHER NATURE ARE MADE HEREUNDER WITH RESPECT TO INFORMATION OR THE PRODUCT TO WHICH INFORMATION REFERS AND NOTHING HEREIN WAIVES ANY OF THE SELLER'S CONDITIONS OF SALE.

Safety Data Sheets providing safety precautions that should be observed when handling and storing our products are available online or by request. You should obtain and review available material safety information before handling our products. If any materials mentioned are not our products, appropriate industrial hygiene and other safety precautions recommended by their manufacturers should be observed.

© 2013 Eastman Chemical Company. Eastman, The results of insight, and Tritan are trademarks of Eastman Chemical Company.